

**schedule 10 for Plain-End Pipe**  
**(Data from ASME B36.10 (incorporating ASTM A53 Table 2.2))**

DN	NPS	Outside Diameter		Wall Thickness		Plain End Mass		Identification	Schedule No.
		mm	in	mm	in	kg/m	lb/ft		
6	1/8	10.3	0.405	1.24	0.049	0.28	0.19		10
8	1/4	13.7	0.540	1.65	0.065	0.49	0.33		10
10	3/8	17.1	0.675	1.65	0.065	0.63	0.42		10
15	1/2	21.3	0.840	2.11	0.083	1.00	0.67		10
20	3/4	26.7	1.050	2.11	0.083	1.28	0.86		10
25	1	33.4	1.315	2.77	0.109	2.09	1.41		10
32	1 1/4	42.2	1.660	2.77	0.109	2.69	1.81		10
40	1 1/2	48.3	1.900	2.77	0.109	3.11	2.09		10
50	2	60.3	2.375	2.77	0.109	3.93	2.64		10
65	2 1/2	73.0	2.875	3.05	0.120	5.26	3.53		10
80	3	88.9	3.500	3.05	0.120	6.46	4.34		10
90	3 1/2	101.6	4.000	3.05	0.120	7.41	4.98		10
100	4	114.3	4.500	3.05	0.120	8.37	5.62		10
125	5	141.3	5.563	3.4	0.134	11.56	7.78		10
150	6	168.3	6.625	3.4	0.134	13.83	9.30		10
200	8	219.1	8.625	3.76	0.148	19.97	13.41		10
250	10	273.0	10.750	4.19	0.165	27.78	18.67		10
300	12	323.8	12.750	4.57	0.180	35.98	24.19		10
350	14	355.6	14.000	6.35	0.250	54.69	36.75		10
400	16	406.4	16.000	6.35	0.250	62.65	42.09		10
450	18	457	18.000	6.35	0.250	70.57	47.44		10
500	20	508	20.000	6.35	0.250	78.56	52.78		10
550	22	559	22.000	6.35	0.250	86.55	58.13		10
600	24	610	24.000	6.35	0.250	94.53	63.47		10
650	26	660	26.000	7.92	0.312	127.36	85.68		10
700	28	711	28.000	7.92	0.312	137.32	92.35		10
750	30	762	30.000	7.92	0.312	147.29	99.02		10
800	32	813	32.000	7.92	0.312	157.25	105.69		10
850	34	864	34.000	7.92	0.312	167.21	112.36		10
900	36	914	36.000	7.92	0.312	176.97	119.03		10